

### Diablillos Phase 1 Drilling - Summary of Highlighted Intercepts

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t
19-001	166	231	Oxides	65	105	0.2	-	120	1.6
19-002	137.5	155	Oxides	17.5	604	0.1	-	612	8.2
	242	257	Oxides	15	286	10.4	-	1,066	14.2
	367	376	Sulphides	9	49	7.3	1.28	729	9.72
20-001	261	290	Mixed	29	430	4.3	2.77	1,037	13.8
	including 261	275	Transition	14	197	6.4	2.53	937	12.5
	including 275	290	Sulphides	15	658	2.4	5.10	1,363	18.2
20-002	337	349	Sulphides	12	13	1.1	2.56	362	4.8
20-003	70	87	Oxides	17	21	2.3	-	195	2.6
	267	289	Oxides	22	25	4.2	-	342	4.6
	405	407	Sulphides	2	28	3.3	4.49	741	9.9
20-004	276	286	Oxides	10	28	1.4	-	133	1.8
20-005	25.5	36	Oxides	10.5	26	1.7	-	152	2.0
	179	184	Oxides	5	192	0.1	-	202	2.7
20-006	206	249	Oxides	43	64	0.7	-	119	1.6
	259	284	Oxides	25	44	1.5	-	153	2.0
	267	275	Oxides	8	44	3.1	-	280	3.7
	including 273	275	Oxides	2	56	9.5	-	765	10.2
20-007	157	218	Oxides	61	256	0.3	-	275	3.7
	including 178	206	Oxides	28	383	0.3	-	409	5.5
	260	262	Sulphides	2	28	23.4	-	1,783	23.8
20-008	352	360	Sulphides	8	-	1.7	2.01	331	4.4
20-009	171	254	Oxides	83	289	1.5	-	398	5.3
	275	280	Oxides	5	99	4.2	-	411	5.5
	287	289	Sulphides	2	55	5.3	2.04	662	8.8
20-010A	149.5	176.5	Oxides	27	167	-	-	167	2.2
	210	257	Oxides	47	96	3.4	-	349	4.7
	261	276	Sulphides	15	296	2.2	-	458	6.1
	316.5	320.5	Sulphides	4	30	4.1	1.52	497	6.6
20-012	150.5	176	Oxides	25.5	33	1.0	-	110	1.5
	183.5	185	Oxides	1.5	154	3.5	-	414	5.5
20-013	291.5	307	Oxides	15.5	14	1.9	-	153	2.0
	438	451	Sulphides	13	8	0.5	0.86	136	1.8

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t
including	441	447	Sulphides	6	23	0.9	1.34	226	3.0
20-015	92	101.5	Oxides	9.5	68	1.1	-	151	2.0
20-017	13	74	Oxides	61	105	1.1	-	190	2.5
including	42	55	Oxides	13	142	2.0	-	294	3.9
20-018	6	22.5	Oxides	16.5	114	1.1	-	198	2.6
including	6	12	Oxides	6	233	2.9	-	450	6.0
20-019	147.5	171.5	Sulphides	24	35	0.2	1.49	205	2.7
20-020	3	24	Oxides	21	132	2.9	-	352	4.7
including	3	16.5	Oxides	13.5	179	4.5	-	515	6.9
20-022	9.5	23	Oxides	13.5	31	2.9	-	251	3.3
20-024	83	110	Oxides	27	86	0.5	-	126	1.7
including	104	110	Oxides	6	168	0.2	-	179	2.4
20-025	58	64.5	Oxides	6.5	226	-	-	226	3.0
	83	105.5	Oxides	22.5	49	0.6	-	91	1.2
	143.3	154.5	Oxides	11.2	222	-	0.06	228	3.0
20-026	130	195	Oxides	65	151	1.9	-	292	3.9
Including	162	189	Oxides	27	208	4.3	-	530	7.1
Including	175	189	Oxides	14	236	6.7	-	741	9.9
20-027	141	244	Oxides	103	389	1.7	-	516	6.9
Including	141	163	Oxides	22	413	0.1	-	424	5.7
Including	163	180	Oxides	17	1,467	0.6	-	1,508	20.1
Including	166	168	Oxides	2	5,796	0.9	-	5,867	78.2
Including	181	244	Oxides	63	95	2.6	-	287	3.8
Including	190	244	Oxides	54	103	2.8	-	316	4.2
Including	231	238	Oxides	7	132	5.4	-	533	7.1
	250.5	256.6	Oxides	6	181	1.0	-	256	3.4
20-028	70	81	Oxides	11	89	1.2	-	177	2.4
	139	142	Oxides	3	37	5.5	-	451	6.0
Including	141	142	Oxides	1	66	12.8	-	1,026	13.7
20-030	205.5	218	Oxides	12.5	33	4.7	-	384	5.1
	260	264.5	Sulphides	4.5	11	3.2	-	270	3.6
20-032	56	73	Oxides	17	8	1.6	-	131	1.7
21-001	33	79	Oxides	46	70	0.8	-	133	1.8
21-002	132	147	Oxides	15	701	0.1	-	711	9.5
Including	132	142	Oxides	10	1,004	0.1	-	1,017	13.6

June 07, 2021

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t
Including	132	134	Oxides	<b>2</b>	1,955	0.3	-	<b>1,975</b>	<b>26.3</b>
	219	271.8	Oxides	<b>52.8</b>	127	2.1	-	<b>286</b>	<b>3.8</b>
	226	246	Oxides	<b>20</b>	185	3.2	-	<b>424</b>	<b>5.7</b>
21-003	106	142	Oxides	<b>36</b>	370	0.4	-	<b>399</b>	<b>5.3</b>
Including	118	122	Oxides	<b>4</b>	635	0.6	-	<b>677</b>	<b>9.0</b>
Including	132	137	Oxides	<b>5</b>	1,556	1.2	-	<b>1,645</b>	<b>21.9</b>
	207	252	Oxides	<b>45</b>	146	0.3	-	<b>172</b>	<b>2.3</b>
Including	217	226	Oxides	<b>9</b>	233	1.1	-	<b>318</b>	<b>4.2</b>
21-004	142	159	Oxides	<b>17</b>	44	1.6	-	<b>161</b>	<b>2.1</b>
	184	192	Oxides	<b>8</b>	82	8.0	-	<b>680</b>	<b>9.1</b>
	239	245	Sulphides	<b>6</b>	63	4.4	0.7	<b>463</b>	<b>6.2</b>
Including	243	245	Sulphides	<b>2</b>	143	11.2	1.3	<b>1,116</b>	<b>14.9</b>
21-005	58	77	Oxides	<b>19</b>	31	4.7	-	<b>380</b>	<b>5.1</b>
Including	58	71	Oxides	<b>13</b>	34	6.4	-	<b>517</b>	<b>6.9</b>
	323.5	344	Sulphides	<b>20.5</b>	25	2.2	-	<b>191</b>	<b>2.6</b>
	327.5	336	Sulphides	<b>8.5</b>	33	4.0	-	<b>334</b>	<b>4.5</b>
	395	412	Sulphides	<b>17</b>	-	0.6	1.2	<b>163</b>	<b>2.2</b>
21-006	103	118	Oxides	<b>15</b>	80	0.1	-	<b>89</b>	<b>1.2</b>
21-007	91	127	Oxides	<b>36</b>	71	0.13	-	<b>81</b>	<b>1.1</b>
21-008	84	119	Oxides	<b>35</b>	39	1.0	-	<b>116</b>	<b>1.6</b>
Including	84	96.5	Oxides	<b>12</b>	38	2.6	-	<b>235</b>	<b>3.1</b>
21-009	208	283	Oxides	<b>75</b>	167	2.2	-	<b>335</b>	<b>4.5</b>
Including	225	263	Oxides	<b>38</b>	184	2.6	-	<b>379</b>	<b>5.1</b>
Including	273	283	Oxides	<b>10</b>	111	6.3	-	<b>586</b>	<b>7.8</b>
Including	274	280	Oxides	<b>6</b>	154	9.8	-	<b>887</b>	<b>11.8</b>
	312.4	314.4	Sulphides	<b>2</b>	24	5.3	1.7	<b>593</b>	<b>7.9</b>
21-010	208	210	Oxides	<b>2</b>	296	4.0	-	<b>596</b>	<b>8.0</b>
	241	260	Oxides	<b>19</b>	13	1.1	-	<b>93</b>	<b>1.2</b>
21-011	111.5	133.5	Oxides	<b>22</b>	48	0.7	-	<b>102</b>	<b>1.4</b>
	235.5	254	Sulphides	<b>18.5</b>	61	1.7	-	<b>189</b>	<b>2.5</b>
Including	247.5	254	Sulphides	<b>6.5</b>	85	4.2	-	<b>402</b>	<b>5.4</b>
21-012	134	238	Oxides	<b>104</b>	216	2.2	-	<b>382</b>	<b>5.1</b>
Including	172	219	Oxides	<b>47</b>	280	4.3	-	<b>600</b>	<b>8.0</b>
Including	204	219	Oxides	<b>15</b>	302	8.0	-	<b>902</b>	<b>12.0</b>
21-013	144	178	Oxides	<b>34</b>	27	0.6	-	<b>71</b>	<b>1.0</b>

**ABRASILVER**

RESOURCE CORP

June 07, 2021

	236	269	Oxides	<b>33</b>	13	0.9	-	<b>82</b>	<b>1.1</b>
21-014	79	156	Oxides	<b>77</b>	149	0.7	-	<b>202</b>	<b>2.7</b>
Including	91	98	Oxides	<b>7</b>	970	2.6	-	<b>1,167</b>	<b>15.6</b>
Including	79	103	Oxides	<b>24</b>	327	2.2	-	<b>494</b>	<b>6.6</b>
	282	347	Oxides	<b>65</b>	16	2.7	-	<b>217</b>	<b>2.9</b>
Including	296	302	Oxides	<b>6</b>	17	6.3	-	<b>486</b>	<b>6.5</b>
Including	323	332	Oxides	<b>9</b>	26	6.5	-	<b>514</b>	<b>6.9</b>
21-015	120	202	Oxides	<b>82</b>	103	2.7	-	<b>305</b>	<b>4.1</b>
Including	138	169	Oxides	<b>31</b>	71	3.1	-	<b>302</b>	<b>4.0</b>
Including	173	199	Oxides	<b>26</b>	140	4.8	-	<b>499</b>	<b>6.7</b>
Including	185	188	Oxides	<b>3</b>	250	23.5	-	<b>2,014</b>	<b>26.9</b>

**Notes**

All results are rounded. Assays are uncut and undiluted. Intervals are drilled widths, not true widths. AgEq calculations for reported drill results are based on USD \$20.00/oz Ag, \$1,500/oz Au and \$3.00/lb Cu. The calculations assume 100% metallurgical recovery and are indicative of gross in-situ metal value at the indicated metal prices. The most recent technical report for the Diablillos Project is the 2018 Preliminary Economic Assessment (PEA) authored by Roscoe Postle Associates Inc. The PEA assumes average metallurgical recoveries of 82% Ag and 86% Au. No metallurgical testwork has yet been completed on the recovery of copper.